

TEST REPORT

Laboratory evaluation of a flooring system

Tests performed according to ASTM E303 standards

Report Number R18194US-A1

Product Flecks 50/50
Flecks Systems, Inc

Flecks TPR Fines
Flecks Systems, Inc

Client Bill McGrath
Flecks Systems, Inc

Date January 8th, 2019

This report contains 2 pages in total. Reproduction of this report is authorized only in its entire form. Results reported are valid only for the products tested. To declare the conformity (or not), the uncertainty of the results was not taken into account. Detailed results are available on request.

LABOSPORT, THE WORLD LEADING SPORTS SURFACES EXPERT

LABOSPORT USA • 1806 S. Dixie Highway • 30720 • Dalton • Georgia • USA
Email : contact@labosport.com • Telephone : 706.529.9474

www.labosport.com



INFORMATION

Product description	Thermoplastic rubber flooring System			
Manufacturer	Flecks Systems, Inc			
Product Name(s)	Flecks 50/50		Flecks TPR Fines	
Sample Numbers	CAN003287		CAN003288	
Thickness	15 mm			
Date of reception	January 7 th 2018			
Date of the tests	January 2018			
Temperature (°C)	Min	23	Max	24
Humidity (%)	Min	48	Max	50



Flecks 50/50



Flecks TPR Fines

RESULTS

Property	Method	Units	Condition	Results	
				50/50	TPR Fines
Sliding properties	EN 13036-4 / ASTM E303	Pendulum Testing Value (PTV)	Dry	95	99
			Wet	83	83
		Dynamic Coefficient of Friction (DCOF)	Dry	1.0	1.0
			Wet	0.8	0.8

REPORTED BY

Daniel Po
(Laboratory Technician) - Writer

Thomas Amadei, T.P.
(Laboratory Manager) - Approver